

آلیژ	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Sn	Pb
ADC6	1.0	0.8	0.1	0.4-0.6	2.5-4.0	-	0.1	0.4	-	0.1	-
ADC10	7.5-9.5	1.3	2.0-4.0	0.5	0.3	-	0.5	1/0	-	0.3	-
ADC12	9.6-12.0	1.3	1.5-3.5	0.5	0.3	-	0.5	1/0	-	0.3	-
LM2	9.0-11.5	1.0	0.7-2.5	0.5	0.3	-	0.5	2/0	0.2	0.1	0.3
LM4	4.0-6.0	1.0	2.0-4.0	0.2-0.6	0.2	-	0.3	0.5	0.2	0.1	0.1
LM6	10.0-13.0	0.6	0.1	0.5	0.1	-	0.1	0.1	0.2	0.05	0.1
LM13	10.0-13.0	1/0	0.7-1.5	0.5	0.8	-	0.2	0.5	0.2	0.1	0.1
LM21	5.0-7.0	1/0	3.0-5.0	0.2-0.6	0.1-0.3	-	0.3	0.2	0.2	0.1	0.2
LM24	7.50-9.50	1.3	3.00-4.00	0.5	0.3	-	0.5	3/0	0.2	0.2	0.3
LM26	8.5-10.5	0.5	2.0-4.0	0.5	0.5-1.5	-	1/0	1/0	0.2	0.1	0.1
LM27	6.0-8.0	0.8	1.5-2.5	0.2-0.6	0.35	-	0.3	1/0	0.2	0.1	0.2
LM28	17.0-20.0	0.7	1.3-1.8	0.6	0.8-1.3	0.6	0.8-1.3	0.2	0.2	0.1	0.1
356.0	6.5-7.5	0.6	0.25	0.35	0.2-0.45	-	-	0.35	0.25	-	-
356.1	6.5-7.5	0.5	0.25	0.35	0.25-0.45	-	-	0.35	0.25	-	-
356.2	6.5-7.5	0/13-0/25	0.1	0.05	0.3-0.45	-	-	0.05	0.2	-	-
A356.0	6.5-7.5	0.2	0.2	0.1	0.25-0.45	-	-	0.1	0.2	-	-
A356.2	6.5-7.5	0.12	0.1	0.05	0.3-0.45	-	-	0.05	0.2	-	-
357.1	6.5-7.5	0.12	0.05	0.03	0.45-0.6	-	-	0.05	0.2	-	-
A357.0	6.5-7.5	0.2	0.2	0.1	0.4-0.7	-	-	0.1	0.04-0.2	-	-
A357.2	6.5-7.5	0.1	0.1	0.05	0.4-0.7	-	-	0.05	0.04-0.2	-	-
358.0	7.6-8.6	0.3	0.2	0.2	0.4-0.6	0.2	-	0.2	0.1-0.2	-	-
380/0	7.5-9.5	2/0	3.0-4.0	0.05	0.1	-	0.5	3/0	-	0.35	-
380.2	7.5-9.5	0.7-1.1	3.0-4.0	0.1	0.1	-	0.1	0.1	-	0.1	-
A380.0	7.5-9.5	1.3	3.0-4.0	0.5	0.1	-	0.5	3/0	-	0.35	-
A413.0	11.0-13.0	1.3	1.0	0.35	0.1	-	0.5	0.5	-	0.15	-
A413.1	11.0-13.0	1/0	1/0	0.35	0.1	-	0.5	0.4	-	0.15	-
A413.2	11.0-13.0	0.6	0.1	0.05	0.05	-	0.05	0.05	-	0.05	-
A-S5U3	4.5-6.0	0.8	2.8-3.8	0.2-0.6	0/05-0/25	-	0.3	0.5	0.25	0.05	0.1
AS5U3G	4.5-6.0	0.6	2.6-3.6	0.45	0.15-0.4	-	0.1	0.2	0.2	0.05	0.1
AS7G	6.5-7.5	0.55	0.15	0.5	0.2-0.4	-	0.05	0.1	0.05-0.25	0.05	0.05
AS7U3G	6.5-8.0	0.8	2.3-3.8	0.3-0.6	0.25-0.6	-	0.3	0.5	0.25	0.1	0.1
AS7GO3	6.5-7.5	0.2	0.1	0.1	0.25-0.4	-	0.05	0.1	0.08-0.25	0.05	0.05
AS9	8.0-10.0	0.6	0.1	0.3	0.1	-	0.05	0.15	0.15	0.05	0.05
AS9U3	8.0-10.0	1/0	2.7-3.7	0.6	0.1-0.3	-	0.5	1.2	0.2	0.2	0.2
ALSi9Mg	9.0-10.0	0.18	0.05	0.1	0.25-0.45	-	-	0.07	0.15	-	-